

※ 通過量(%)

区分	mesh	4	6	8	10	14	20	28	35	48	65	100	150	200	270	Pan	化学組成		
	μm	4,750	3,350	2,360	1,700	1,180	850	600	425	300	212	150	106	75	53		SiO2	Al2O3	Fe2O3
乾燥 珪砂	K-0																71.54	14.61	1.64
	K-1		65.00	5.00													73.62	13.94	1.07
	K-2			61.00	1.00												73.76	14.07	1.04
	K-3				52.00	2.00											75.88	12.99	0.9
	KY-3					75.00	3.00										76.76	12.65	0.8
	K-4						73.00	2.00									76.58	12.76	0.81
	K-5							60.00	3.00								76.15	13.06	0.9
	K-6								70.00	9.00							72.48	14.78	1.34
	K-7									96.00	54.10	20.00	7.00	2.00			69.56	15.8	2.2
建設 骨材	特砂	100		90.3	78	66.3	57.00	38.80	26.30	19.50	11.10	5.50	5.10	1.70	0.50				
	珪砂1号	100		96.3	87.7	78.3	70.30	55.30	39.90	31.30	20.90	13.30	3.90	1.70	0.80				

(JIS A 1102 骨材ふるい分け試験による)